

TPU—T3385



Technical Data Sheet

Thermoplastic Polyurethane

- **Application:** Accessories, Compounding, Caster wheel etc.
- **Description:** Polyester-based TPU
- **Processing methods:** Injection mould.
- **Characteristics:** Excellent physical properties, Easy&stable processing, Hydrolysis resistance and reusable properties.
- **Properties:**

Item	Test Method	Value
Yellow index(Yi)	ASTM-E313	0-2
Specific gravity(g/cm ³)	ASTM-D792	1.22
Hardness(Shore A)	ASTM-2240	85±1
Tensile strength(Mpa)	ASTM-D412	32
100% Modulus(Mpa)	ASTM-D412	7.5
300% Modulus(Mpa)	ASTM-D412	12
Elongation at break(%)	ASTM-D412	586
Teat strength (KN/m)	ASTM-D624	105
Flowing beginning Point.(°C)	/	186
Processing temperature (°C)	/	195-215

■ Processing & Guide

For optimum results, previous drying of the product 2-3 hours under 100~110°C is advisable, in a hot air circulatory, vacuum desiccate-air dryer.

■ Package & Storage

25kg/bag.

Never put opened packages exposed in open air for prolonged periods of time during processing. Because of the high moisture absorbing property, TPU products should be well stored in a dry, cool and shady area.

■ Note

These are typical values and should not be used as specifications.

SHANDONG INOV POLYURETHANE CO., LTD.

Add: Polymer and Auxiliary Material Zone, High-Tech District, Zibo City, Shandong Province,
China Tel: +86-533-3598719
Web: <http://www.inov-chem.com>