



The Polyolefin Company (Singapore) Pte. Ltd.

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720
Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293 2748
Plant : 401 Ayer Merbau Road, Singapore 628285
Website: www.tpc.com.sg

Co. Reg. No.: 198001666D

COSMOPLENE[®] FC9415G

CHARACTERISTICS

COSMOPLENE FC9415G is a Polypropylene Random Copolymer specially designed for PP woven cloth coating with low coating temperature, high bonding strength, small neck-in and higher coating speed.

APPLICATIONS

Extrusion coating for PP woven bag, cloth/paper sandwich for chemical and cement bag.

FC9415G complies with U.S. FDA Regulation 21 CFR 177.1520 (C) 3.1a, as long as it is used unmodified and processed according to standard manufacturing practices in the industries.

Note : Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact article.

PHYSICAL PROPERTIES

ITEM	UNIT	FC9415G	TEST METHOD
Melt Flow Rate	g/10 mins	30	ASTM D1238
Density	g/cm ³	0.90	ASTM D792
Tensile Strength at break	MPa	25	ASTM D638
Elongation at break	%	850	ASTM D638
Stiffness	MPa	730	ASTM D747
Melting Point	°C	136	TPC METHOD

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.



Dec 2014

COSMOPLENE[®]
POLYPROPYLENE

COSMOTHENE[®]
LOW DENSITY POLYETHYLENE

COSMOTHENE[®] EVA
ETHYLENE VINYL
ACETATE COPOLYMER